



Case Study in Thailand-5

LAB Test Parameter	"Before Status" (sample 88172)	End of Trial (sample 96149)
VsPI TM (VPI+sPI / 2)	56 (67.1 / 44.6)	33 (46.7 / 19.8)
TAN	0.28	0.14
Water Separability Time (mins) to 40/40/0 ml	30	7.5
Water Separability D1401 (emulsion ml at 5 mins.)	54	20
Air Release Time (secs)	254	77
Foaming Tendency Sequence I,II,III	620 ml / 50 ml / 780 ml	350 ml / 30ml / 100ml
Gravimetric Patch Appearance		

Oil Sample Data Shows Improvement

